

Original Article

Comparison of the cyclic fatigue resistance of ProGlider, PathGlider and One G path-finding instruments

Damla Özsu Kırıcı^{1*} • Ertuğrul Karataş² • Ahmet Demirhan Uygun³ • Ezgi Doğanay Yıldız⁴ • Kezban Meltem Çolak² • Hakan Arslan²

¹Department of Endodontics, Faculty of Dentistry, Akdeniz University, Antalya, Turkey

²Department of Endodontics, Faculty of Dentistry, Atatürk University, Erzurum, Turkey

³Department of Endodontics, Faculty of Dentistry, Afyon Kocatepe University, Turkey

⁴Department of Endodontics, Faculty of Dentistry, Kırıkkale University, Kırıkkale, Turkey

*Corresponding Author; E-mail: d_ozsu@hotmail.com

Received: 7 September 2018; Accepted: 21 December 2018

J Dent Res Dent Clin Dent Prospect 2019; 13(1):57-60|doi: 10.15171/joddd.2019.009

This article is available from: <https://joddd.tbzmed.ac.ir>

© 2019 Özsu Kırıcı et al. This is an Open Access article published and distributed by Tabriz University of Medical Sciences under the terms of the Creative Commons Attribution License (<http://creativecommons.org/licenses/by/4.0>), which permits unrestricted use, distribution, and reproduction in any medium, provided the original work is properly cited.

Abstract

Background. The aim of the present study was to compare the cyclic fatigue resistance of novel nickel titanium rotary path-finding instruments.

Methods. Twenty instruments were selected for each file system. A simulated stainless steel root canal, with a 90° angle of curvature and a curvature radius of 3 mm, was used for cyclic fatigue test of the ProGlider (#16, progressive taper: 0.02–0.085), PathGlider (#15, taper: .03), and One G (#14, taper: .03) instruments. Statistical analyses were performed with one-way ANOVA (P=0.05). Post hoc Tukey tests were used to determine any statistically significant differences between the groups.

Results. The ProGlider instruments exhibited significantly more cyclic fatigue resistance than both PathGlider and One G instruments (P<0.001). One G instruments had significantly more resistance to fracture than PathGlider instruments (P<0.05).

Conclusion. ProGlider instruments had better cyclic fatigue resistance than PathGlider and One G instruments.

Key words: Cyclic fatigue, ProGlider, PathGlider, One G.

Introduction

The introduction of nickel-titanium (NiTi) instruments, which are commonly used in current endodontic practice, has revolutionized root canal preparation. These instruments result in less canal transportation and more dentin conservation, reduce the risk of zipping or stripping curved canals, exhibit and more elasticity and flexibility.¹⁻⁵ Despite these advantages, NiTi instruments may fracture within the

root canal without any sign of previous permanent deformation.⁶⁻⁸ Two different mechanisms have been identified for the fracture of rotary NiTi instruments: torsional failure and cyclic fatigue.^{4,9} The former occurs when the tip of the instrument binds in the canal while the shank continues to rotate, whereas the latter occurs when the instrument rotates freely in a curvature, generating tension/compression cycles in the region of maximum flexure until fracture occurs.^{10,11}

Creating a glide path is an indispensable step to understanding the original anatomy of the root canal¹²

and provides less apical extrusion of debris¹³ and canal transportation.¹⁴ Recently, several NiTi glide-path instruments have been developed. PathGlider (Komet, Brasseler, Lemgo, Germany) is a novel single-file (#015 or #020) path-finding system with a non-cutting instrument tip and kite-shaped cross-sectional design. One G (Micro-Mega, Besançon Cedex, France) is also a single-file path-finding system, with an asymmetrical cross-sectional design. According to the manufacturer, the One G instruments have a variable pitch between each cutting edge, which limits the screwing effect.

To date, no studies have investigated the cyclic fatigue resistance of PathGlider system. Therefore, the present study aimed to compare the cyclic fatigue resistance of these path-finding instruments with that of ProGlider (Dentsply Maillefer, Ballaigues, Switzerland) and One G instruments. The null hypothesis was that there would be no difference in the cyclic fatigue resistance among the tested instruments.

Methods

A total of 20 instruments were selected for each file system and visually inspected under a stereomicroscope at a magnification of $\times 20$. Defective samples were discarded and new instruments without any defects replaced the defective samples.

A simulated stainless steel root canal with a 90° angle of curvature and a curvature radius of 3 mm was used for the cyclic fatigue test of the ProGlider (#16, progressive taper: 0.02–0.085), PathGlider (#15, taper: 0.03) and One G (#14, taper: 0.03) instruments. All the instruments were placed in the canal up to the

center of the curvature, which was 4 mm from the tip of the file. During testing, a synthetic oil (KaVo Dental GmbH, Biberach, Germany) was sprayed into the artificial canal for lubrication. The instruments were rotated at a speed of 300 rpm and 2.5 Ncm torque with an X-Smart motor (X-Smart, Dentsply Maillefer) until fracture occurred. The time to fracture was recorded in seconds using a chronometer. The motor was operated and timing was launched after the instruments had been positioned in the artificial canals as described above. As soon as the fracture of the instrument was detected visually and audibly, timing was stopped and the time to fracture was recorded in seconds. The cyclic fatigue test of all the instruments was performed by one operator.

Statistical Analysis

Statistical analyses were performed with one-way ANOVA ($P=0.05$). Post hoc Tukey tests were used to determine any statistically significant differences between the groups. All the statistical analyses were performed using SPSS 20 (IBM SPSS Inc., Chicago, IL, USA).

Results

Figure 1 shows the cyclic fatigue resistance values for each group. Statistical analysis revealed significant differences between the groups in terms of mean time to fracture ($P<0.05$). The ProGlider instruments exhibited significantly more cyclic fatigue resistance than PathGlider and One G instruments ($P<0.001$). There was also a significant difference between PathGlider and One G groups. One G instruments had




Figure 1. Mean times to fracture in seconds for the ProGlider, PathGlider and One G groups.

significantly more resistance to fracture than PathGlider instruments ($P < 0.05$). In other words, ProGlider instruments had the highest cyclic fatigue resistance, followed by One G and PathGlider instruments.

Discussion

The null hypothesis was refuted because there were statistically significant differences between the tested instruments in terms of cyclic fatigue resistance. According to the results of the present study, ProGlider instruments had the highest resistance to cyclic fatigue. ProGlider instruments are manufactured from a heat-treated M-wire alloy. Several studies have shown that instruments manufactured with conventional NiTi wire are less resistant to cyclic fatigue than those made of M-wire alloy.¹⁵⁻¹⁹ The difference between the manufacturing processes might explain the increased cyclic fatigue resistance of ProGlider instruments. Additionally, while ProGlider instruments have a taper of 0.02 at the first 4 mm from the tip, PathGlider and One G instruments have an 0.03 taper. In other words, the diameter of ProGlider instruments at 4 mm from the tip of the file are less than the diameter of PathGlider and One G instruments at 4 mm from the tip of the file. Previously, it has been reported that increased instrument diameter is inversely related to the cyclic fatigue life span of rotary instruments.²⁰

Although PathGlider and One G files have the same taper, there was also a statistically significant difference between these instruments in terms of cyclic fatigue resistance. PathGlider instruments have a kite-shaped cross-sectional design, whereas the cross-sectional design of One G instruments is asymmetrical. Previously, it has been reported that the cyclic fatigue resistance mainly depends on the cross-sectional area and flexibility of the file.^{21,22} Differences in cross-sectional designs of these instruments might explain the present results. Moreover, the cyclic fatigue resistance of a file is also affected by its helical angle²³ and number of threads.²⁴ It can be speculated that the variable pitch design of One G instruments might have provided increased cyclic fatigue resistance. Since there are no previous studies on the cyclic fatigue resistance of PathGlider and One G instruments, a direct comparison cannot be performed.

In the current study, a standardized artificial root canal machined in a steel block was used for the cyclic fatigue test, as in several previous studies.^{16,19,25,26} The limitation of this method is that the artificial canal allows the file extreme flexibility apically at the point of the curvature, because of the width of the canal.¹⁹ However, the simulated artificial canal minimizes the

effect of other mechanisms of instrument fracture, aside from cyclic fatigue.²⁷ Since all the instruments were rotated at a speed of 300 rpm, the number of cycles to fracture were not calculated.

Conclusion

ProGlider instruments exhibited better cyclic fatigue resistance than PathGlider and One G instruments. One G instruments had significantly more resistance to fracture than PathGlider instruments.

Acknowledgements

The work was supported by the Atatürk University, Department of Scientific Research Projects.

Ethical approval

This article does not contain any studies with human participants or animals.

Conflict of interests

The authors deny any conflict of interests.

Authors' contributions

D.K, E.K, A.D.U, H.A designed the study. D.K, E.K., A.D.U, MC and E.D contributed to the material and method stage and writing stage. H.A and E.D analysed the data. Both authors have read and approved the final manuscript.

References

- Esposito PT, Cunningham CJ. A comparison of canal preparation with nickel-titanium and stainless steel instruments. *J Endod*, 1995, 21(4): 173-176. DOI:10.1016/S0099-2399(06)80560-1
- Himel VT, Ahmed KM, Wood DM, Alhadainy HA. An evaluation of nitinol and stainless steel files used by dental students during a laboratory proficiency exam. *Oral Surg Oral Med Oral Pathol Oral Radiol Endod*, 1995, 79(2): 232-237.
- Taschieri S, Necchi S, Rosano G, Del Fabbro M, Weinstein R, Machtou P. [Advantages and limits of nickel-titanium instruments for root canal preparation. A review of the current literature]. *Schweiz Monatsschr Zahnmed*, 2005, 115: 1000-1005.
- Parashos P, Messer HH. Rotary NiTi instrument fracture and its consequences. *J Endod*, 2006, 32 (11) : 1031-1043. DOI: 10.1016/j.joen.2006.06.008
- Altunbaş DA, K.E. Kuştarıcı, A. AN IN VITRO STUDY OF THE EFFECTS OF DIFFERENT TORQUE VALUES APPLIED TO THE NICKEL TITANIUM ROTARY CANAL INSTRUMENTS FOR CURVED ROOT CANAL PREPARATION. *Atatürk Üniversitesi Diş Hekimliği Fakültesi Dergisi*, 2015, 25: 172-180.
- Pruett JP, Clement DJ, Carnes DL, Jr. Cyclic fatigue testing of nickel-titanium endodontic instruments. *J Endod*, 1997, 23(2): 77-85. DOI: 10.1016/S0099-2399(97)80250-6
- Arens FC, Hoen MM, Steiman HR, Dietz GC, Jr. Evaluation of single-use rotary nickel-titanium instruments. *J Endod*, 2003, 29(10): 664-666. DOI:10.1097/00004770-200310000-00013

8. Ok EE, H. Uysal, B. EFFECT OF SEPARATED ROTARY INSTRUMENTS ON THE APICAL MICROLEAKAGE OF ROOT CANAL FILLINGS. *Atatürk Üniversitesi Diş Hekimliği Fakültesi Dergisi*, 2014, 24: 246-251
9. Sattapan B, Palamara JE, Messer HH. Torque during canal instrumentation using rotary nickel-titanium files. *J Endod*, 2000, 26: 156-160.
10. Sattapan B, Nervo GJ, Palamara JE, Messer HH. Defects in rotary nickel-titanium files after clinical use. *J Endod*, 2000, 26(3): 161-165. DOI: 10.1097/00004770-200003000-00008
11. Martin B, Zelada G, Varela P, Bahillo JG, Magan F, Ahn S, Rodriguez C. Factors influencing the fracture of nickel-titanium rotary instruments. *Int Endod J*, 2003, 36(4): 262-266.
12. Berutti E, Negro AR, Lendini M, Pasqualini D. Influence of manual preflaring and torque on the failure rate of ProTaper rotary instruments. *J Endod*, 2004, 30(4): 228-230. DOI:10.1097/00004770-200404000-00011
13. Topcuoglu HS, Duzgun S, Akpek F, Topcuoglu G, Akti A. Influence of a glide path on apical extrusion of debris during canal preparation using single-file systems in curved canals. *Int Endod J*, 2015. DOI:10.1111/iej.12484
14. Elnaghy AM, Elsaka SE. Evaluation of root canal transportation, centering ratio, and remaining dentin thickness associated with ProTaper Next instruments with and without glide path. *J Endod*, 2014, 40: 2053-2056. DOI: 10.1016/j.joen.2014.09.001
15. Capar ID, Ertas H, Arslan H. Comparison of cyclic fatigue resistance of nickel-titanium coronal flaring instruments. *J Endod*, 2014, 40(8): 1182-1185. DOI: 10.1016/j.joen.2013.12.031
16. Larsen CM, Watanabe I, Glickman GN, He J. Cyclic fatigue analysis of a new generation of nickel titanium rotary instruments. *J Endod*, 2009(3), 35: 401-403. DOI: 10.1016/j.joen.2008.12.010
17. Bouska J, Justman B, Williamson A, DeLong C, Qian F. Resistance to cyclic fatigue failure of a new endodontic rotary file. *J Endod*, 2012, 38(5): 667-669. DOI:10.1016/j.joen.2012.01.016
18. Capar ID, Ertas H, Arslan H. Comparison of cyclic fatigue resistance of novel nickel-titanium rotary instruments. *Aust Endod J*, 2015, 41(10): 24-28. DOI:10.1111/aej.12067
19. Capar ID, Kaval ME, Ertas H, Sen BH. Comparison of the cyclic fatigue resistance of 5 different rotary pathfinding instruments made of conventional nickel-titanium wire, M-wire, and controlled memory wire. *J Endod*, 2015, 41: 535-538. doi: 10.1016/j.joen.2014.11.008
20. Parashos P, Gordon I, Messer HH. Factors influencing defects of rotary nickel-titanium endodontic instruments after clinical use. *J Endod*, 2004, 30: 722-725.
21. Kim TO, Cheung GS, Lee JM, Kim BM, Hur B, Kim HC. Stress distribution of three NiTi rotary files under bending and torsional conditions using a mathematic analysis. *Int Endod J*, 2009, 42(1): 14-21. doi: 10.1111/j.1365-2591.2008.01481.x
22. Kim HC, Yum J, Hur B, Cheung GS. Cyclic fatigue and fracture characteristics of ground and twisted nickel-titanium rotary files. *J Endod*, 2010, 36(1): 147-152. DOI: 10.1016/j.joen.2009.09.037
23. He R, Ni J. Design improvement and failure reduction of endodontic files through finite element analysis: application to V-Taper file designs. *J Endod*, 2010, 36: 1552-1557. DOI: 10.1016/j.joen.2010.06.002
24. Versluis A, Kim HC, Lee W, Kim BM, Lee CJ. Flexural stiffness and stresses in nickel-titanium rotary files for various pitch and cross-sectional geometries. *J Endod*, 2012, 38: 1399-1403. DOI: 10.1016/j.joen.2012.06.008
25. Karatas E, Arslan H, Buker M, Seckin F, Capar ID. Effect of movement kinematics on the cyclic fatigue resistance of nickel-titanium instruments. *Int Endod J*, 2016,49(4). DOI: 10.1111/iej.12453
26. Arslan H, Alsancak M, Doganay E, Karatas E, Davut Capar I, Ertas H. Cyclic fatigue analysis of Reciproc R25(R) instruments with different kinematics. *Aust Endod J*, 2016, 42(1). DOI: 10.1111/aej.12115
27. Yao JH, Schwartz SA, Beeson TJ. Cyclic fatigue of three types of rotary nickel-titanium files in a dynamic model. *J Endod*, 2006, 32(1): 55-57. DOI: 10.1016/j.joen.2005.10.013